



Cromamig 625

GMAW - MIG MAG
Stainless Steel

Date:	2013-05-27
Revision:	9

Description:

Cromamig 625 is primarily intended for welding Inconel 625 and similar composition nickel base alloys which are used for their excellent corrosion and oxidation resistance combined with an exceptionally high resistance to pitting corrosion and chloride induced stress corrosion cracking. Very suitable for a wide range of dissimilar joint combinations between nickel base alloys, mild and low alloy steels and stainless steels, especially where high temperature service conditions prevail.

Applications:

Suitable for welding the nickel base alloys 625 and 825 but also 6 Mo steels (ASTM S31254) and 9% Ni steels for cryogenic applications. Overlay welding of carbon or low alloy steels and dissimilar joints.

Welding current:

DC+

Wire composition, wt.%

	C	Si	Mn	P	S	Cr	Ni
Min						20,0	60,0
Typical	0,01	0,10	0,05	0,005	0,005	22,0	64,0
Max	0,03	0,50	0,50	0,015	0,015	23,0	

	Mo	Cu	Al	Ti	Fe	Nb ²
Min	8,0					3,15
Typical	9,0	0,10	0,070	0,18	0,3	3,6
Max	10,0	0,50	0,40	0,40	5,0	4,15

Shielding gas:

I3, Ar + <30% He, 20-25 l/min

Corrosion resistance

Very good resistance to general and intergranular corrosion. Maximum resistance (practically immune) to pitting corrosion, crevice corrosion and stress corrosion cracking in chloride bearing environments.

Scaling temperature:

The weld metal is resistant to oxidation in air up to 1150°C. (Very high tensile strength and yield strength up to approx. 850°C. Rp 0.2%=300 MPa, Rm=400 MPa)

Chemical composition, wt.%

	C	Si	Mn	P	S	Cr	Ni
Min							
Typical	0,01	0,10	0,05	0,005	0,005	22,0	64,5
Max							

	Mo	Cu	Al	Ti	Fe	Nb ²
Min						
Typical	9,0	0,10	0,02	0,10	0,3	3,5
Max						

² Nb + Ta

Mechanical properties

	<u>Specified</u>	<u>Typical</u>
Yield strength, Rp0.2%:		480 MPa
Tensile Strength, Rm:	≥ 760 MPa	780 MPa
Elongation, A5	≥ 30%	40%
Impact energy, CV:		20°C • 110 J -196°C • 60 J

Classification:

EN ISO 18274 S Ni 6625 (NiCr22Mo9Nb)
AWS A5.14 ERNiCrMo-3

Approvals:

TüV
CE

Note

Ta max 0.30

Product data:

Diam.mm	Product code	Spool weight	Dip Current A	Dip Voltage V	Spray Current A	Spray Voltage V
0,8	98202008	15 kg S300	60-100	18-21	150-170	24-26
1,0	98202010	15 kg S300	75-140	18-21	170-200	26-28
1,2	98202012	15 kg S300	130-160	18-21	175-250	26-28