

Cromacore DW 308LP

FCAW - Flux cored arc welding Stainless Steel

Description:

Cromacore DW 308LP is a rutile flux cored wire intended for welding the 18% Cr / 10% Ni type stainless steels. The wire has been specially designed for fully positional welding at high welding currents. Suitable also for stabilised grades 347 and 321 if service temperature is below 400 °C. Cromacore DW 308LP operates with a very stable, spatter free arc and produces a bright, smooth weld bead surface and self-releasing slag. Ideal for high productivity welding in the vertical position.

Welding positions:



Welding current:

DC+

Deposition efficiency: 87%

Shielding gas:

M21, 80% Ar + 20% CO2, 22-25 l/min C1, 100% CO2, 22-25 l/min Stick-out:

15-25 mm

Ferrite content: FN 9

Chemical composition, wt.%

| | С | Si | Mn | Р | S | Cr | Ni |
|---------|------|-----|-----|-------|-------|------|------|
| Min | | | 0.5 | | | 18.0 | 9.0 |
| Typical | 0.03 | 0.7 | 1.5 | 0.020 | 0.010 | 19.6 | 9.9 |
| Max | 0.04 | 1.0 | 2.0 | 0.030 | 0.025 | 21.0 | 11.0 |

| | Мо | Cu | V | Nb |
|---------|-----|------|-----|------|
| Min | | | | |
| Typical | 0.1 | 0.05 | 0.1 | 0.08 |
| Max | 0.5 | 0.5 | 0.2 | 0.1 |

Mechanical properties

| | Specified | Typical |
|-------------------------|-----------|--------------|
| Yield strength, Rp0.2%: | | 400 MPa |
| Tensile Strength, Rm: | ≥ 520 MPa | 590 MPa |
| Elongation, A5 | ≥ 35% | 41% |
| Impact energy, CV: | | –20 ℃ • 40 J |
| | | |

Classification:

AWS A5.22

ISO 17633-A

Approvals:

GL

CE

TUV


09140.00

E 308LT1-4/-1


T 19 9 L P M/C 1

4550S

Recommended parameter range:



Deposition rate per hour:



Product data:

| Diam.mm | Product code | Spool weight |
|---------|--------------|--------------|
| 1,2 | 95771012 | 15 kg BS300 |
| 1,2 | 95771112 | 5 kg BS200 |

Note

- Strip:
- S ≤ 0.03% P ≤ 0.04%
- N ≤ 0.06%
- 11 ≤ 0.00

Date:

Revision:

2013-05-27 13